

## EUROPEAN REACTION TO FIRE CLASSIFICATION REPORT ACCORDING TO THE EUROPEAN STANDARD EN 13501-1

Notified Body by the French State besides the European Commission under number : 0071

Product standard : NF EN 14041  
Resilient, textile and laminate floorcoverings

(free translation of French classification report n° F050699 CEMATE/8)

**N°F050699 - CEMATE/9**

**Material submitted by :** GERFLOR  
50 Cours de la République  
69627 VILLEURBANNE Cedex

**Commercial trademark :** ATTRACTION

**Production site :** GERFLOR  
Z.I. du Bois des Lots  
26130 SAINT PAUL TROIS CHATEAUX  
FRANCE

**Brief description :** Floorcovering in PVC

**Date of report :** 2005, June 14<sup>th</sup>

**Only full reproduction of the present document is authorized.  
It contains 4 pages**

## 1. INTRODUCTION

This classification report defines the classification assigned to product in accordance with the procedures given in EN 13501-1.

## 2. DETAILS OF CLASSIFIED PRODUCT

### 2.1. NATURE AND END USE APPLICATION

VFHE type (NF EN 649 standard) floorcovering  
 Tiles tested with a joint to 250 mm – free standing

### 2.2. DESCRIPTION

Characteristics of the product :

Product	Thickness in mm Tolerance : -0.10/+0.13 mm	Mass per unit square meter in g/m <sup>2</sup> Tolerance : -10/+13 %
ATTRACTION	5.00	7420

Product	Wear layer Plasticized PVC  Thickness in mm	PVC intercalary with fillers calendered with reinforced glass fibers  Thickness in mm	Backing Under layer in calendered PVC with fillers  Thickness in mm
ATTRACTION	1.00	1.00	3.00

Text report to be followed on next page

### 3. TEST REPORTS AND TEST RESULTS IN SUPPORT OF THIS CLASSIFICATION

#### 3.1. TEST REPORTS

Name of laboratory	Name of sponsor	Test report ref. n°	Test method
LABORATOIRE NATIONAL D'ESSAIS 29 av. Roger Hennequin 78197 TRAPPES CEDEX	GERFLOR 50 Cours de la République 69627 VILLEURBANNE Cedex	File : F050699 CEMATE/5 Date of tests : 2005/05/10 and 20 2005/06/07	Radiant panel EN ISO 9239-1

#### 3.2. TEST RESULTS FOR FLOORINGS

Test methods	Number of tests	Parameters	Results
EN ISO 9239-1 Free standing to a particle board non-FR	1  <b>ATTRACTION</b> (5 specimens)	Critical flux (kW/m <sup>2</sup> ) Smoke (%.min)	<b>7.62</b> <b>531</b>

Text report to be followed on next page

**4. CLASSIFICATION AND DIRECT FIELD APPLICATION**

**4.1. CLASSIFICATION**

Fire behaviour	Smoke production	Flaming droplets
<b>C<sub>fl</sub></b>	<b>s1</b>	-

**4.2. FIELD OF APPLICATION**

This classification is valid for the products mentioned in § 2.2 or strictly and equally stipulated in the quoted production site.

Colour : various

Thickness : about 5.00 mm

Free standing to a particle board non FR and A1 and A2 classified substrates

**5. LIMITATIONS**

**5.1. RESTRICTIONS CONCERNING THE VALIDITY PERIOD OF THE CLASSIFICATION REPORT**

None.

**5.2. WARNING**

This document does not represent type approval or certification of the product.


Trappes, the 14<sup>th</sup> of June 2005

The Head of Fire Behaviour Division

Test Officer

  
Alain SAINRAT





Luc CHEVALIER